



OMRI Listed Granular TRIO®



PROPERTY	RANGE	TYPICAL	GUARANTEE
K	18.2-18.4%	18.3%	18.2% min.
K ₂ O	22.0-22.2%	22.1%	22.0% min.
Mg	10.8-11.7%	11.2%	10.8% min.
MgO	17.9-19.4%	18.6%	17.9% min.
S	22.0-22.4%	22.2%	22.0% min.
SO_4	66.0-67.2%	66.6%	66.0% min.
Chloride		1.0%	
Moisture	0.1 - 0.5%	0.25%	
SGN		260	
UI		40	

PARTICLE SIZE DISTRIBUTION

TYLER MESH	OPENING MM	TYPICAL % CUMULATIVE
+6	3.330	21
+8	2.360	67
+10	1.68	95
+14	1.18	99
+20	0.85	100

TYPICAL BULK DENSITY

93 lbs/ft³ 1490 kg/m³

TYPICAL ANGLE OF REPOSE 34-37 DEGREES

East Plant 210 Red Cloud Road Carlsbad, New Mexico 88220 575.234.3872 Direct to Plant 800.451.2888 Customer Service

TYPICAL CHEMICAL ANALYSIS			
K	18.3%		
Ca	0.1%		
Na	0.5%		
Insoluble	0.7%		
рН	7		

OMRI LISTED For Organic Use



The information shown in this data sheet represents average properties of product analyses of composite samples and typical analyses should not be considered a guaranteed specification. Individual shipment and grab sample analyses may fall outside of the above typical values due to natural variability within the product. Additional handling, transportation, or improper/extended storage may affect product analyses. Intrepid Potash disclaims any responsibility or liability for any loss or damage that may occur from any reliance on, or other use of, the above information with respect to the product.







